Technical Data



BR3DGY01-UV-TOUGH UV DLP **Tough** 3D polymers



SPECS

FEATURES

Photocentric's range of Tough UV DLP photopolymers are ideal for making objects where you want flexibility and strength. Thick objects are stiff but can be made to bend and flex under strain and will return to their original shape. They exhibit moderate to high tensile shear properties and moderate to high elongation, objects can be bent with medium-high force. UV Tough provides excellent imaging in your desktop DLP printer. You will experience the benefits of fast exposure times and a wide exposure latitude, allowing you to hold the finest details your machine can provide. The solid material is tough, durable and long lasting provided it is stored in dry conditions away from strong UV light.

PROCESSING INSTRUCTIONS

Follow the procedures laid out in your 3D DLP printer user manual. Resin should be poured into the tray away from direct sunlight. Resin can also be reused but should be poured through a filter to remove solid lumps. Keep hood on at all times to avoid unwanted curing or contamination. Liquid polymer is soluble in water and soap. After making clean, objects surface tack can be removed by leaving under water in UV for 20 minutes or longer. If any surface tack persists you can remove it by wiping the parts with IPA.

DATA

Viscosity (At 25°C Brookfield spindle 3)	470 cPs
Hardness (After post exposure)	60 Shore D
Tensile strength ASTM D638 (After post expose	35 MPa ure)
Tensile strength ASTM D638 (Before post expo	10 MPa osure)
Elongation at break ASTM D638	50%
Heat deflection temp ASTM D648	N/A
Storage	10 <t>50°C</t>
Density	1.14 g/cm ³

AVAILABLE COLOURS

Grey Other colours available on request

Available in 1kg bottles with non-drip cap.

Photocentric Ltd. Cambridge House, Oxney House Peterborough PE1 5YW **UK** email: *info@photocentric.co.uk* Photocentric Inc. 2205 West Parkside Lane, Phoenix, 85027, AZ **USA** email *info@photocentricusa.com*